

# Solid Carbide Drills

## Speed and Feed Recommendations

List No. 5374 Standard Length GP • List No. 5375 Screw Machine Length • List No. 5376 Straight Flute

Workpiece Material	Brinell Hardness (BHN)	Morse List No.	Surface Speed (SFM)	FEED PER REVOLUTION BY DRILL DIAMETER (IPR)			
				1/16"	1/8"	1/4"	1/2"
Low Carbon Steel 1018, 12L12, 1108, 1213	≤ 120	5374	250	0.0015	0.0030	0.0040	0.0080
		5375					
		5376					
Low & Medium Carbon Steel 1018, 1551, 11L44	120 - 250	5374	225	0.0020	0.0040	0.0060	0.0110
		5375					
		5376					
Medium Carbon and Alloyed Steel 1040, 1140, 4340, 8640	≤ 250	5374	200	0.0015	0.0030	0.0040	0.0080
		5375	150	0.0015	0.0030	0.0040	0.0080
		5376					
Tool and Die Steels P20, A2, D2, H12	≤ 250	5374	200	0.0015	0.0030	0.0040	0.0080
		5375					
		5376					
Tool and Die Steels P20, A2, D2, H12	250 - 350	5374	150	0.0010	0.0020	0.0030	0.0060
		5375	125	0.0010	0.0020	0.0030	0.0060
		5376	125	0.0010	0.0020	0.0030	0.0060
Hard Materials, Alloys, Tool Steels 40 Rockwell C and Higher	—	5374					
		5375					
		5376	60	0.0005	0.0010	0.0015	0.0020
Free Machining Stainless Steels 303,410, 416, 440F	≤ 260	5374	100	0.0010	0.0020	0.0030	0.0060
		5375	100	0.0010	0.0020	0.0030	0.0060
		5376					
Moderate Machining Stainless Steels 304, 316	≤ 300	5374					
		5375	75	0.0010	0.0020	0.0030	0.0060
		5376	75	0.0010	0.0020	0.0030	0.0060
Difficult Machining Stainless Steels 17-4PH, 316L, AM350	≤ 450	5374					
		5375	60	0.0010	0.0020	0.0030	0.0060
		5376	60	0.0010	0.0020	0.0030	0.0060
Cast Iron - Soft Gray	≤ 160	5374	250	0.0015	0.0030	0.0040	0.0080
		5375	275	0.0020	0.0040	0.0060	0.0110
		5376	275	0.0015	0.0030	0.0040	0.0080
Cast Iron - Gray	160 - 260	5374	250	0.0015	0.0030	0.0040	0.0080
		5375	275	0.0020	0.0040	0.0060	0.0110
		5376	250	0.0015	0.0030	0.0040	0.0080
Cast Iron - Ductile	250	5374	180	0.0015	0.0030	0.0040	0.0080
		5375	180	0.0020	0.0040	0.0060	0.0110
		5376	175	0.0015	0.0030	0.0040	0.0080
Cast Iron - Malleable	250 - 330	5374	180	0.0015	0.0030	0.0040	0.0080
		5375	180	0.0020	0.0040	0.0060	0.0110
		5376	180	0.0015	0.0030	0.0040	0.0080
Titanium Alloys Commercially Pure 99.0	110 - 170	5374					
		5375	50	0.0005	0.0010	0.0020	0.0045
		5376	50	0.0005	0.0010	0.0020	0.0045
Titanium Alloys Ti-6Al-4V, ASTM B367 Grades C-3, C-4	≤ 250	5374					
		5375	50	0.0005	0.0010	0.0020	0.0045
		5376	50	0.0005	0.0010	0.0020	0.0045
High Temperature Alloys Inconel, Hastelloy, Waspaloy	150 - 250	5374					
		5375	60	0.0005	0.0010	0.0020	0.0045
		5376	60	0.0005	0.0010	0.0020	0.0045
Aluminum Alloys 2025, 6061, A140, 514.0	≤ 150	5374	350	0.0020	0.0040	0.0060	0.0110
		5375					
		5376					
Copper Alloys Brass and Bronze	≤ 200	5374	80	0.0020	0.0040	0.0060	0.0110
		5375					
		5376					
Composites & Plastics	≤ 128	5374	175	0.0010	0.0020	0.0030	0.0060
		5375					
		5376					
Magnesium Alloys AZ80A, HM12A, AM60A, ZE41A	50 - 90	5374	325	0.0020	0.0040	0.0060	0.0110
		5375					
		5376					

SPEEDS and FEEDS are suggested starting points only and may be increased or decreased depending on actual material and machining conditions. Start conservatively and increase speed and feed until drilling cycle is optimized.