

Cutting Speeds	Workpiece Material	Brinell Hardness (BHN)	Surface Speed (SFM)
	Aluminum Alloy Castings	—	40-95
	Gray Cast Iron	≤ 230	45-70